



THE SCIENTIFIC AND TECHNICAL RESEARCH COUNCIL OF TURKEY
MARMARA RESEARCH CENTER

FOOD INSTITUTE

P.K 21, 41470 GEBZE/KOCAELI
T 0 262 677 20 00 F 0 262 641 23 09
<http://mam.tubitak.gov.tr>

TEST/ANALYSIS/MEASUREMENT REPORT

(Industrial Services)

Report No : 49362558-125.05- 97 / **381**
Report Date : **23/01/2020**
Requested by : KONTENSAN KONYA TENEKE KUTU AMB. VE MAK. SAN. VE TİC. A.Ş
Adress : 2. O.S.B KIRIM CAD. NO:4 SELÇUKLU KONYA
Subject : PACKAGING ANALYSES

The results in this report are valid only for the analyzed samples

Approved by

Dr. Neşe Aslı ÖNCÜ

Assigned for Industrial Services

This report and results can not be used for commercial and advertisement purposes by the demanding enterprise or its customers. Complete or part of this report cannot be copied or published.
The marked (*) analyses are accredited. Analysis reports without authorized signature are not legitimate.

This report is prepared as 2 originals (1 for the customer, 1 for the institute archives) and contains 3 pages

Page 1 / 3



Report No : 49362558-125.05- 97 / **381**
Requested by : KONTENSAN KONYA TENEKE KUTU AMB. VE MAK. SAN. VE TİC. A.Ş.
Adress : 2. O.S.B KIRIM CAD. NO:4 SELÇUKLU KONYA


Sample : TIN BOX-NON LACQUERED PRODUCT
Parti / Lot No :
Number of Samples: 15
Sample handling : By Cargo
Condition of samples at reception:Paper Packaking

Expiry Date :
Production Date :
Institute sample register no:20-13/001
Reception date and time : 06/01/2020 14:00:00
Date of the analysis : 07/01/2020 - 23/01/2020

Information on retention samples : () Sample returne to the costumer () Retention sample available (x) Retention sample is not taken

Analysis	Result	Limits	Method
Tin determination in tinplate	6 g/m ²	Minimum:2.3 g/m ²	ASTM B 767-88

Notes

Authorized Signatures:

53455

This report and results can not be used for commercial and advertisement purposes by the demanding enterprise or its customers.
Complete or part of this report cannot be copied or published.
The marked (*) analysis are accredited.
Analysis reports without authorized signature are not legitimate.

This report is prepared as 2 originals (1 for the customer, 1 for the institute archives) and contains 3 pages Page 2 / 3




Report No : 49362558-125.05- 97 / 381
Requested by : KONTENSAN KONYA TENEKE KUTU AMB. VE MAK. SAN. VE TIC. A.Ş.
Adress : 2. O.S.B KIRIM CAD. NO:4 SELÇUKLU KONYA

Sample : TIN BOX-LACQUERED PRODUCT
Parti / Lot No :
Number of Samples: 15
Sample handling : By Cargo
Condition of samples at reception:Paper Packaking
Expiry Date :
Production Date :
Institute sample register no:20-13/002
Reception date and time : 06/01/2020 14:00:00
Date of the analysis : 07/01/2020 - 23/01/2020

Information on retention samples : () Sample returne to the costumer () Retention sample available (x) Retention sample is not taken

Analysis	Result	Limits	Method
Tin determination in tinplate	6.2 g/m ²	Minimum:2.3 g/m ²	ASTM B 767-88
Lacquer determination in tinplate	10.3 g/m ²		ASTM B 767-88

Notes

Authorized Signatures:

53455

This report and results can not be used for commercial and advertisement purposes by the demanding enterprise or its customers.
Complete or part of this report cannot be copied or published.
The marked (*) analysis are accredited.
Analysis reports without authorized signature are not legitimate.

This report is prepared as 2 originals (1 for the customer, 1 for the institute archives) and contains 3 pages Page 3 / 3